
Product Information

Product: Mg unbleached paper

Table of contents:

Unbleached Cellulose Fibre **93.95%**

Consists of:

Softwood/Hardwood 99.9%

Chemical additives: 0.1%

This chemical is used to prevent foaming in the washing process.

Consists of:

Mineral oil >90%

Fatty acid-derivatives 5%

Emulsifier <5%

Chemical Additives **approx. <0.05%**

A type of mineral oil is sprayed towards the drying cylinder of the paper machine.

This chemical makes the paper web release from the cylinder surface and it stays only on the cylinder and is not going into the paper web.

Water **6%**

Heavy Metals **<100ppm**

Concentrations less than 100ppm for the following heavy metals:

Cadmium, Lead, Mercury, Chrome, Molybdenum